

試驗報告



報告編號：TB-16-05466X

C-16-19586

頁數：1 OF 1

報告日期：105年10月06日

工程名稱：自測

承包商：-----

委託單位：鴻佳國際股份有限公司

供料廠商：-----

樣品名稱：複合木質地板 8 mm (Modern Plank)

送驗人員：鴻佳國際股份有限公司-黃淑琴

收件日期：105年09月23日

試驗日期：105年09月23日~105年10月06日

備註：1.以上資料由顧客提供(收件及試驗日期除外)

2.除非另有說明，此報告結果僅對測試之樣品負責

未經本公司事先書面同意，此報告不可部分複製

試驗結果：

試驗項目	試驗結果	CNS 7614(1994) 防焰一級規範值	CNS 7614(1994) 防焰二級規範值	CNS 7614(1994) 防焰三級規範值	試驗方法
火源加熱時間 (sec)	60	-----	-----	-----	CNS 7614(1994) A法
餘焰時間 (sec)	0.0	≤ 1	≤ 5	≤ 5	
餘燼時間 (sec)	0.0	≤ 60	≤ 60	≤ 60	
炭化長度 (cm)	4.7	≤ 5	≤ 10	≤ 15	

註：1.樣品平均厚度 8.1 mm

2.試驗者：周上筆

3.樣品厚度大於CNS 7614(1994)所規定之允許最大厚度，故無法出具TAF標誌之報告

-----oOo-----

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準。

報告簽署人

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.